

Table 1. SSDA ATC-24 TESTS AND SUMMARY OF RESULTS

TEST Nos.	BEAM COLUMN	INTERSTORY DRIFT (%) (Qualifying Drift=4%)
17 18	<u>33X141</u> 14X283	4.2 5.1
19 20	<u>27x94</u> 14x176	4.3 5.0
21 22	<u>36x300</u> 14x500	4.5 4.4
23 24	<u>24x94</u> 30x135	4.1 4.1
25 26	<u>36x170</u> 30x235	4.0 4.0
1a	<u>36x256</u> 27x307	4.9
2a 3a	<u>36x393</u> 14x550 - (Gr. 65)	5.1 6.0

Table 1. SSDA ATC-24 TESTS AND SUMMARY OF RESULTS

TEST Nos.	BEAM COLUMN	INTERSTORY DRIFT (%) (Qualifying Drift=4%)
17 18	<u>33X141</u> 14X283	4.2 5.1
19 20	<u>27x94</u> 14x176	4.3 5.0
21 22	<u>36x300</u> 14x500	4.5 4.4
23 24	<u>24x94</u> 30x135	4.1 4.1
25 26	<u>36x170</u> 30x235	4.0 4.0
1a	<u>36x256</u> 27x307	4.9
2a 3a	<u>36x393</u> 14x550 - (Gr. 65)	5.1 6.0